









# All Silica Double Clad Fiber

Passive Double Clad Fiber (SMM900) is a passive, dual cladding, Multimode (MM) fiber that combines both Single-Mode (SM) and MM fiber characteristics within a single fiber. The fiber has a germano-silicate SM core, a pure silica inner cladding to guide the pump light and a fluorine doped secondary cladding to give outstanding power handling over a full range of environmental conditions. The fiber does not rely on a low index polymer coating, so it can be stripped, cleaved and spliced like a standard telecoms fiber, without the need to apply a low index recoat material

SMM900 has been designed specifically to be used in conjunction with Fibercore's Dual Clad Erbium/Ytterbium Doped Fiber (CP1500Y), Multimode Pump Fiber (MM105) and Isolating Wavelength Division Multiplexer (CP-IWDM). In order to minimize losses throughout the system and maximize efficiency, the optical characteristics of these fibers have been matched for high splice compatibility.

#### Advantages:

- · All silica design
- No recoating required
- · Stable in humid environments

### Typical applications:

- Telecoms
- Erbium Doped Fiber Amplifier (EDFA)Cable Television (CATV)
- Fiber laser
- Biomedical illumination

#### Related Products:

- Dual Clad Erbium/Ytterbium Doped Fiber (CP1500Y)
- Large Core Fiber (MM105)
- Isolating Wavelength Division Multiplexer (CP-IWDM)

#### **Product Variant:**

 SMM900 Double clad passive fiber with SM core and MM pump guide

## Specifications

|                            | SMM900              |
|----------------------------|---------------------|
| Single-Mode Core           |                     |
| Mode Field Diameter (μm)   | 6.5 - 8.2 @1550nm   |
| Numerical Aperture         | 0.18 - 0.20         |
| Cut-Off Wavelength (nm)    | 870 - 970           |
| Attenuation (dB/km)        | 4 (nominal) @1550nm |
| Core Concentricity (µm)    | ≤0.75               |
| Pump Guide                 |                     |
| Diameter (µm)              | 100 - 104           |
| Numerical Aperture         | 0.24 - 0.28         |
| General                    |                     |
| Cladding Diameter (µm)     | 125 ± 1             |
| Proof Test (%)             | 1 (100 kpsi)        |
| Coating Diameter (µm)      | 245 ± 7             |
| Coating Type               | Dual Layer Acrylate |
| Operating Temperature (°C) | -55 to +85          |